



Balmer Lawrie & Co. Ltd.

BALSYN[®] MP 1

Characteristics	: Copolymer emulsion with unique softness.
Active matter (% w/w)	: 30 ± 2
pH of 10% solution	: 6.0 – 7.0
Appearance	: Yellowish white emulsion.
Charge / Ionic nature	: Anionic.
Compatibility	: Excellent compatibility with a wide range of mineral tannins, Vegetable extracts, all type of syntans, anionic fatliquors and cationic fatliquors. Easily miscible with cold or hot water.
Properties Imparted	: <ul style="list-style-type: none">• Excellent grain tightness with high degree of soft ness.• Imparts fine, smooth and elastic grain.• Improves glazeability and burnishability of the leathers.• Imparts roundness throughout the leather.
Application	: 4%-8% along with fatliquor for all types of leathers in retanning dyeing and fatliquoring, thereby 2%-3% fatliquor and 1%-3% of syntan can be reduced in your regular process. 2% as a pre fatliquoring cum grain tightening for all types of leathers. 4% in neutralisation bath to get very good milling effect.
Safety	: A non-hazardous, industrial chemical, should be handled with normal care. Any contact with eyes and / or spillage on skin should be washed thoroughly in running water
.Storage	: This product has 6 months shelf life when stored in original packing. Protect from moisture & exposure to sunlight. Avoid freezing. Stir well before use.

[®] Trademark Registration applied for.

Product
October, 2009

All data and recommendations given in this document are for guidance only and we cannot be held responsible in any way whatever.