



**Balmer Lawrie & Co. Ltd.**

## **BALSYN<sup>®</sup> SAR**

Nature of the Product	: Soft acrylic resin
Active content (% w/w)	: 30 ± 2 %
pH of 10% solution	: Approx. 6.5 - 7.0
Appearance	: Pale yellow liquid
Compatibility	: Excellent compatibility with all types of syntan, Chrome, Vegetable tannins, anionic fatliquors and cationic fatliquors. Easily miscible with cold or hot water.
Properties Imparted	: <ul style="list-style-type: none"><li>• Imparts good body when used in chrome tanning as Well as in Re-chroming</li><li>• Imparts filling with softness</li><li>• Improves grain tightness and inducts compactness</li><li>• Imparts fine, smooth and elastic grain</li></ul>
Applications	: In Rechroming 2-4 % for cow softy, goat upper, sheep cabretta, lining, glove & nappa. In retanning 3-6 % for all types of leather.
Safety	: A non-hazardous, industrial chemical should be handled with normal care. Any contact with eyes and or spillage on skins should be washed thoroughly in running stream of water. Incase of ingestion requires immediate medical assistance. Meanwhile give the patient 2-4 glass of warm water and induce vomiting.
Storage	: This product has a shelf life of six months from the date of delivery. Protect from moisture and exposure to sunlight. Avoid freezing. Stirr well before use.

<sup>®</sup> Trademark Registration applied for.

*Product*  
October, 2009

---

All data and recommendations given in this document are for guidance only and we cannot be held responsible in any way whatever.